

Application No. 10/660,461  
Inventor: Christopher J. Calhoun  
Page 3

MA9758P

### Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

#### Listing of Claims

1. (Currently Amended) A method for promoting healing of damaged tissue after an open heart surgery, the method comprising the steps of:

providing a substantially planar healing membrane which is:

- (a) substantially-smooth on at least one side;
- (b) substantially uniform in composition;
- (c) about 10 microns to about 300 microns in thickness;
- (d) non-porous;
- (e) constructed from a resorbable polymer base material ~~comprising at least one consisting essentially of a material selected from the group consisting of a poly-lactide polymer and a poly-lactide copolymer copolymer of two or more lactides;~~ and
- (f) adapted to be resorbed into the mammalian body within a period of approximately 18 to 24 months from an initial implantation of the membrane into the mammalian body; and

placing the healing membrane adjacent to an opening in pericardial tissue of a patient so that the pericardial tissue surrounding the opening can regenerate over the membrane.

2. (Original) The method of claim 1 wherein the resorbable polymer base material comprises 70:30 poly (L-lactide-co-D,L-lactide).

Application No. 10/660,461  
Inventor: Christopher J. Calhoun  
Page 4

MA9758P

3. (Original) The method of claim 1 wherein the resorbable polymer base material comprises poly-L-lactide.
4. (Original) The method of claim 1 wherein the thickness of the membrane is about 100 microns.
5. (Original) The method of claim 1 wherein the thickness of the membrane is about 200 microns.
6. (Original) The method of claim 1 wherein the healing membrane is provided in a sterile packaging.
7. (Original) The method of claim 1 wherein the step of placing the healing membrane in a patient is effective to attenuate formation of scar tissue.
8. (Original) The method of claim 1 wherein the step of placing the healing membrane in a patient is effective to attenuate tissue adhesion.
9. (Original) The method of claim 1 further comprising a step of attaching the healing membrane to the pericardial tissue.
10. (Original) The method of claim 9 wherein the attaching step comprises heat bonding the membrane to the pericardial tissue.
11. (Original) The method of claim 1, wherein the membrane comprises an anti-scar forming agent, including angiotensin antagonists.
- 12-20. Cancelled.

Application No. 10/660,461  
Inventor: Christopher J. Calhoun  
Page 5

MA9758P

21. (Original) The method of claim 1, wherein the resorbable polymer base material comprises copolymers of polycaprolactone and trimethylene carbonate to thereby reduce a stiffness of the substantially planar healing membrane.

22. (Currently Amended) The method of claim 1, wherein the healing membrane is precontoured into a heart-shaped bag ~~to~~ and is placed to surround the apex of a heart.

23. (Currently Amended) The method of claim 1, wherein the healing membrane is precontoured into a tube ~~to facilitate placing the membrane~~ and is placed to around the conduit of a left-ventricular assist device (LVAD).

24. (Currently Amended) The method of claim 1, wherein the healing membrane is precontoured ~~to facilitate placement~~ and is placed over a pump of a left-ventricular assist device (LVAD).